

EXPERIMENTAL STUDY OF PARTIAL REPLACEMENT OF CEMENT AND COARSE AGGREGATE WITH FLY ASH AND COCONUT SHELL

Mukkannan.A¹SwethaSaseendran.k² Vignesh kumar.V³ ChandraMohan.R⁴

¹Assistant Professor^{2,3,4} B.E.Students

^{1,2,3,4}Department of Civil Engineering

^{1,2,3,4}Akshaya College of Engineering and Technology, Coimbatore,Tamilnadu.

Abstract - Properties of concrete with partial replacement of coconut shell as coarse aggregate and fly ash as replacement of cement is studied. In this study M25 grade of concrete was made. Concrete mix of 10%, 20%, 30% and 40% replacement of coconut shell as coarse aggregate and constant replacement of 30% of fly ash were made. Water cement ratio of 0.45 was maintained for all the mix proportions. Properties like compressive strength, split tensile strength and flexural strength were studied at 7, 14, 28 days of curing period and results are analyzed and compared with the regular (conventional) mix. Test for grade as per specified procedure of IS codes. The materials are proportioned by their weight. The water cement ratio is obtained by conducting workability tests. The results found were comparable with that of conventional mix. The proportion used in this study is 1:1.49:3.03 and water cement ratio is 0.47.

1. INTRODUCTION

Today due to the development of the infrastructure the need of concrete has been increased at high rate. Concrete is important construction materials that have been widely used all over the world. The use of

concrete has been increasing day by day. Due to this some negative impacts are there in production of concrete such as coarse aggregate extraction from natural resources, scarcity of river sand it leads to depletion of materials and ecological imbalance. Various researches have been found that replacement for coarse aggregate. The use of plastic, paper and pulp industry waste, textile waste, rice ash, recycled rubber tyres, broken bricks are some examples for replacing aggregate in concrete. Coconut shell is an agricultural by product which can be used as coarse aggregate in concrete. According to report made in 2016 India is the third largest coconut producers in world. India produces of about 119 million tonnes of coconut every year. The coconut shells are accumulated in land and get degraded around 100-120years. Due to this, a serious environment problem of disposal of coconut

shells occurs. So to minimize this coconut shell can be used as aggregate in concrete. The main aim of this project is to study the strength of coconut shell concrete with different replacement percent. Also to attempt has been made to study the suitability of fly ash in concrete.

1.1 AIM AND OBJECTIVE

The aim of study is to evaluate the performance and suitability of coconut shell in concrete with as alternative for coarse aggregate.

To evaluate the compressive strength, split tensile strength, and flexural strength of concrete with replacement

The objectives of experimental study are:

- Study on strength characteristics of M25 grade concrete with replacement of 10%, 20%, 30% and 40% of coarse aggregate by coconut shell
- To determine the %, strength of concrete at 7, 14, 28 days.
- Steel fibers are used to increase the flexural and tensile strength of concrete.
- Admixture is used to minimum the water cement ratio and to achieve the workability.

2. MATERIALS USED

2.1 CEMENT

The available cement 53 grades ordinary Portland cement (OPC) of ULTRATECH brand has been used in the present investigation for all concrete mixes. The cement used was fresh and without any lumps.

2.2 FINE AGGREGATE

Fine sand should consist of natural sand or crushed stone sand. It should be hard, durable and clean and be free from organic matter etc. Fine Sand should not contain any appreciable amount of clay balls and harmful impurities such as alkalis, salts, This fly ash is pozzolanic in nature, and contains less than 20% lime (CaO). coal, decayed vegetation etc.

2.3 COARSE AGGREGATE

The generally aggregate occupy 70% to 80 % of volume of concrete and it have an important influence on its properties of concrete. Coarse aggregate was used of size 20mm conforming and also IS 383 is used. The quality of aggregate is good clean, hard, and also strong, and be free of absorbed harmful chemicals, coatings of clay, other contaminants that can affect hydration of cement or reduce the paste-aggregate bond.

2.4 COCONUT SHELL

Coconut shell is an abundantly available waste material which can be used as potential or replacement material in the construction. Coconut shells were unruined from the local temple after that

it was cleaned, sun dried, removed fibers to evaluate its properties.



2.5 FLY ASH

The burning of harder, older anthracite and bituminous coal typically produces Class F fly ash. The use of fly ash as a partial replacement for Portland cement will usually reduce water demand. Fly ash and lime generates less heat, resulting in reduced thermal cracking when fly ash is used to replace a percentage of Portland cement



2.6 SUPER PLASTICIZER

HI - PLAST SP IS A HIGH RANGE WATER reducing admixture was used. It is brown color liquid based on selected sulphonated naphthalene polymers. This capability exceeds that of normal water- reducing admixtures, resulting in lower dosages and better control. 1% of super plasticizer was used.



2.7 STEEL FIBRE

Steel fibres are made under strict quality control process and gives excellent strength and durability to concrete eliminating cracking. End hooked fibre are used in this experiment which having 30mm length and 0.5mm diameter. Significant use of steel fibre is to improve flexural strength. 1% of steel fibres used in experimental study.



3.0 MIX DESIGN

Concrete mix of M25 grade was designed by conforming to IS 10262-1982 method. The coarse aggregate were replaced with coconut shell by 10%, 20%, 30% and 40%. 30% of fly ash with cement. 0.45 water cement ratio was kept constant.

Table -1: Mix proportion

	cement	Fine aggregate	Coarse aggregate	Water cement ratio

Ratio	1	2.24	2.84	0.43
Mass kg/m ³	385	862	1097	140

Mixes:

M1= normal concrete

M2= 0% of CS+30% of FA+1% SP+1% SF

M3=10% of CS+30% of FA+1% SP+1% SF

M4=20% of CS+30% of FA+1% SP+1% SF

M5=30% of CS+30% of FA+1% SP+1% SF

M6=40% of CS+30% of FA+1% SP+1% SF

Where, CS= Coconut shell

FA= Fly ash

SP= super plasticizers

SF= Super fibres

4. CASTING, CURING AND TESTING OF SPECIMEN

Coconut shell as partial replacement of coarse aggregate and fly ash as cement were used. All ingredients are first dried mixed then water and super plasticizers added. Machine mix is done to get homogenous mixture. Then the mixture is poured into specimens. Vibrators are used for compaction. After vibration the surface of specimen is leveled using trowel. Specimens are kept for drying for 24 hours and then specimen were demoulded. Specimens are then kept for curing. Curing is done 7, 14, 28 days. Testing of specimen: The 9 cubes for each proportions were tested for compressive strength of size 150 × 150 × 150 mm. 6 cylinders for each proportions of size 150mm diameter and 300mm length were casted and used for testing split tensile strength and 6 beams for each proportions of size 500mm length, 100mm width and 100mm depth were casted and used for testing flexural strength at 7, 14, 28 days curing.

4.1 COMPRESSIVE STRENGTH TESTS

Specimens of size 150 × 150 × 150 mm were casted for all the proportions and tested in compression testing machine. Capacity of machine is 2000KN. Compressive strength calculated by using equation,

$$F = P/A$$

Where, F= compressive strength in N/mm²

P= maximum load in Newton

A= cross sectional area in mm²



Table-2 Shows the average compressive strength at various proportions

Mix proportion	7days compressive strength in N/mm ²	14days compressive strength in N/mm ²	28days compressive strength in N/mm ²
Normal concrete	16.25	22.2	31.50
0%	10.97	23.4	33.20

10%	13.23	22.5	35.25
20%	11.2	22.35	35.9
30%	11.11	19.2	31.45
40%	9.33	16.2	28.90

4.2 SPLIT TENSILE STRENGTH TESTS

Specimen of size 150 mm diameters and 300mm length were casted. The test was conducted on the Compression Testing Machine. Cylinder specimens were placed under the Compression Testing Machine in a horizontal direction perpendicular to the direction in which they are casted. The tensile strength was found by using equation,

$$F = 2P/πLd$$

Where, F=tensile strength in N/mm²

P = Maximum load applied

d = measured depth of specimen

L= Length of specimen

Table -3: Shows the average tensile strength of concrete at various proportions

Mix proportions	7days split tensile strength in N/mm ²	14 days split tensile strength in N/mm ²	28 days split tensile strength in N/mm ²
Normal concrete	1.48	2.12	2.45
0%	1.50	1.61	2.85
10%	1.34	1.80	2.90
20%	1.04	1.93	3.0
30%	1.06	1.40	2.4
40%	0.95	1.09	1.90



Mix proportions	7days split tensile strength in N/mm ²	14 days split tensile strength in N/mm ²	28days split tensile strength in N/mm ²
Normal concrete	3.40	4.35	6.2
0%	3.75	3.75	6.9
10%	3.75	7.50	8.45
20%	3.75	7.9	9
30%	3.0	4.75	6.1
40%	1.5	2	4.0

4.3 FLEXURAL STRENGTH TESTS

Concrete as we know is relatively strong in compression and weak in tension. Beams tests are found to be dependable to measure flexural strength property of concrete. The system of loading used in finding out the flexural tension is two points loading. The specimen placed in flexural testing machine in such a manner that the load to be applied to uppermost surface as cast in the mould. The flexural strength was found by using equation,

$$F = PL/bd^2$$

Where, F=Flexural strength in N/mm²

P = Maximum load applied

L = Length of specimen

b = breadth of specimen

d = depth of specimen

Table -4: shows the average flexural strength at various proportions

5. RESULTS AND DISCUSSION

From the experimental analysis, it is an evident that at age of 7, 14, 28 days fig 1,2,3 shows the compressive strength, split tensile strength and flexural strength increases as a percentage of coconut shell is increased. For the further increases of coconut shell the strength decreased. Optimum strength obtained at 20% replacement of coconut shell as coarse aggregate.

6. CONCLUSIONS

Coconut shells can be used as partial replacement for coarse aggregate up to percentage of 10, 20, and 30. More than the 30% replacement decreases in strength is seen. For optimum result the 20% replacement coconut shell is good.

a. It was found that without addition of fly ash; only by replacement of coconut shell strength has decreased at 10% and 20% when compared to normal concrete.

b. When fly ash was replaced for cement along with coconut shell as coarse aggregate replacement the strength property was improved.

c. Light weight concrete can be produced by using coconut shell as coarse aggregate.

d. Increase in percentage of coconut shell, decrease the densities of concrete.

e. Coconut shell with 20% replacement shows a higher strength than normal concrete.

replacement of coarse aggregate with coconut shell in the concrete".

CODE BOOK

© IS CODE 10262:2009 for Concrete Mix Proportion

REFERENCES

[1] Akshay S. Shelke, Kalyani R. Ninghot, Pooja P. Kunjekar, Shraddha P. Gaikwad (2014) International Journal of Civil Engineering Research, "coconut shell as partial replacement for coarse aggregate".

[2] B.Damodhara Reddy, S.Aruna Jyothy, Fawaz Shaik (2014) IOSR Journal of Mechanical and Civil

Engineering, "experimental analysis of the use of coconut shell as coarse aggregate".

[3] Dr. B. Rajeevan and Shamjith K M (2014) International Journal of Engineering Research & Technology (IJERT), "a study on the utilization of coconut shell as coarse aggregate in concrete".

[4] Jyothi Kamal and J.P. Singh (2015) International Journal of Innovative Research in Science, Engineering and Technology, "experimental study on strength characteristics of m20 concrete with partially replacement of coarse aggregate with coconut shell and cement with fly ash".

[5] Md Taquiuddin, Nikita Munigal, Imtiyaz Ahmed, Sharnappa (2015) International Journal for Innovative Research in Science & Technology, "study on strength characteristics of concrete with partial replacement of cement with fly ash and coarse aggregate with coconut shell".

[6] R. Thenmozhi and N. Balasubramani (2015) Nature Environment and Pollution Technology, "Experimental Study on Self Compacting Concrete (M25) with 25% Fly ash Incorporating 10% Replacement of Coconut-Shell as Coarse Aggregate".

[7] R. D. Padhye, N. S. Deo (2016) International Journal of Engineering Research, "cement replacement by fly ash in concrete".

[8] Shrikant M. Harle (2017) Journal of Research in Engineering and Applied Sciences, "partial