

# Effects of Temperature, Concentration of Catalyst and Reaction Time on Biodiesel Production From Gossipium Hirsutum Seed

Yaro, M. N.

**Abstract-** Gossipium hirsutum (cotton) seeds were collected and processed. 500.00 g of the processed cotton seeds were subjected to soxhlet extraction for 5 hours at 85°C using absolute methanol (as extracting solvent). The extract (cotton seed oil) was recovered from extracting solvent by rotary evaporation and concentrated to a constant weight at 37°C. A solution mixture of volume ratio, 1: 9 of cotton seed oil to methanol was prepared and subjected to transesterification reaction under different operational conditions of temperature, concentration of catalyst (KOH) and reaction time for biodiesel production. The biodiesel produced was separated from the associated product (glycerol). The excess methanol containing biodiesel produced was removed by distillation. The saponification value of the glycerol component of the transesterification product was determined. The work showed that the optimum operational conditions for maximum biodiesel production were 65°C, 1.00 M of KOH (as catalyst) and 65 minute. The work also showed that: temperature above 65°C led to decomposition of biodiesel; catalyst concentrations above 1.00 M led to formation of soap as by-product and; prolonging of reaction time beyond 65 minute led to hydrolysis of the biodiesel formed.

**Keywords-** Gossipium hirsutum seed; seed oil; transesterification reaction; biodiesel; glycerol; saponification value, operational conditions.

## INTRODUCTION

Presently, Nigeria is in the grip of an unprecedented energy crises caused by the political influence on fuel supply and distribution by the major and independent petroleum products marketers. There is also the problem of face-up between the oil-rich communities and the Federal Government of Nigeria due to long time neglect of the region in terms of infrastructural development and environmental pollution (Ndana and Manko, 2010). In addition, the hike price of fossil fuels (petrol, diesel, kerosene, liquefied natural gas, e.t.c.), which are difficult to get by the majority of common people also contributes nuisance in using these fuels (Ekwenchi and Yaro, 2010). The interest in adopting the use of renewable energy came to the fore during the worldwide energy crisis of the 1970s when high fuels (oil and gas) demand highlighted the world's dependence on fossil fuels in which the rate of consumption was much faster than it was drilled from the earth crust, which may result in the depletion of fossil fuels supply all over the world (Ndana and Manko, 2010). Population growth worldwide, which led to high energy demand, environmental problem and health hazards associated with the use of fossil fuels also fronted the search for renewable energy sources as alternative to popular conventional fossil fuels (Sani, et al, 2014). In order to overcome or minimize the aforementioned

problems associated with the drilling, refining and combustion of fossil fuels, as well, as to succeed in achieving alternative renewable energy sources (biodiesel inclusive), there is the need to embark on research and exploitation of seed oils from renewable biomass resources in our natural environment. This can be achieved by domesticating and growing viable plants as energy crops on our endowed vast land ( Garba et al, 2012). Some common raw material for biodiesel production include : soya beans, palm oil, shear butter oil, poultry oil, fish oil, groundnut oil, algae, Jatropha curcas seed oil, Gossipium hirsutum seed oil, sesame oil and sorghum ( Pinto et al, 2005).

Biofuels are generally alternative renewable energy sources, which are environmentally-friendly due to their biodegradability and low emission of carbon (ii) Oxide, sulphur-free quality and non toxic nature ( Sani et al, 2014). Biodiesel was found to be promising alternative to popular fossil fuels, as it possesses all the properties of the conventional diesel, such as high flash point and improved cetane number (Shajaratun et al, 2014). Biodiesel is a clean burning fuel produces through transesterification reaction between triglycerides (TGs) and short chain alcohol (methanol or ethanol) in the presence of catalyst. The process of biodiesel production (i.e. transesterification reaction) is achieved through various methods such as base catalyzed transesterification, direct acid catalyzed transesterification or conversion of oil to fatty acid and subsequently to biodiesel (Ndana and Manko, 2010).

The chemistry of biodiesel production through transesterification reaction involves deprotonation of alcohol with a base and become a very strong electrophile.

The base serves as a catalyst, which helps the transesterification reaction between TGs and short chain alcohol (usually methanol) to quickly occur and form ester of fatty acid (biodiesel) and glycerol (trihydric alcohol) according to the equation below as reported by Nasar et al (2016).



During transesterification of TGs into biodiesel, some of the biodiesel formed decomposed into glycerol at temperature above 65oC ; more TGs participate in saponification reaction with the catalyst at high concentration of base

catalyst and; extension of reaction time leads to hydrolysis of ester into TGs, which subsequently produces soap (Garba et al, 2012).

The major focus of recent advancement is the development of recyclable heterogeneous solid acid catalyst (SACs) for easier production of biodiesel. These catalysts have been established as favourable alternative to commercially used catalyst for biodiesel production (Nasar et al, 2016). SACs both the Bronsted-type (such as sulphonic acid containing materials) and Lewis-type (such as mixed sulphated oxides) combined the advantages of heterogeneous base catalysts and mineral acids (Choundan and Sarma, 2011). The exceptional advantages to this particular class of catalyst (SACs) are insensitivity to moisture and simultaneous esterification and transesterification reactions as can be seen in the following schematic reaction diagram as reported by Nasar et al (2016):

$R_1 = \text{alkyl esters of triglyceride}$

Elimination of the final biodiesel washing step, minimizing of corrosion problem even in the presence of acid species, selectivity, recyclability and easy regeneration of catalyst after use are also advantages of SACs (Guo et al, 2012). Another advantage of SACs is its ability to sterically hinder salvation of the catalytic active sites from the action of water, which helps in minimizing catalyst deactivation, minimizing of product (biodiesel) contamination as a result of easy separation from the reaction medium (Nusterer et al, 1996). In addition, the applicability and hydrophobic surface of SACs, which prevents the polar by-products (water and glycerol) from deactivating the active sites, which in return enhances selectivity adsorption of oily hydrophobic molecules to the surface of the catalyst as reported by Choundan and Sarma, (2011). These advantages among many others attracted attention in considering solid acid catalysed biodiesel production much over base catalysed process on low grade feedstock (Nasar et al, 2016).

However, very little has been done on the mechanism and reaction pathways of TGs on SACs during the production of biodiesel. These short comings together with some other technological challenges necessitated the adoption of predominantly conventional method of biodiesel production. (i.e. base catalysed transesterification method) in the present work. This work reports studies on the effects of temperature, reaction time and concentration of catalyst on the production of biodiesel and glycerol from Gossipium hirsutum seed oil and The work also reports studies on the quantitative determination of soap generated under these operational conditions.

## Materials and Methods

### Collection and Processing of Experimental

#### Sample

Dried cotton (*Gossipium hirsutum*) seeds were collected from a cotton processing factory in Malumfashi Local Government Area, Katsina State, Nigeria. The seeds were ground using grinding machine and sieved to a particle size of less than  $250 \times 10^{-6}$  m using mesh according to the method described by Ekwenchi et al (1998) with few adjustments.

#### Extraction of Cotton Seed Oil

A mass (500.00 g) of ground *Gossipium hirsutum* seeds were subjected to soxhlet extraction for 5 hours at 85°C using absolute methanol. The extract (cotton seed oil) was recovered from the extracting solvent (methanol) by rotary evaporation and concentrated to a constant weight at 37°C on hot plate in fume cupboard.

#### Preparation of Solution Mixture

A solution mixture was prepared by mixing of methanol with cotton seed oil in the volume ratio (1:9) of cotton seed oil to methanol according to the method described by Garba et al (2012) with few adjustments.

#### Effect of Temperature on Biodiesel Production

A volume of solution mixture (400.00 cm<sup>3</sup>) containing 10.00 cm<sup>3</sup> of 1M KOH (as catalyst) was place in a reactor (500.00 cm<sup>3</sup> round bottomed flask). The mixture was heated on a hot plate at 35oC along with stirring using magnetic stirrer at the rate of 450 rpm. The heating and stirring were stopped when 2 distinct liquid phases were formed, which were allowed to cool and settle. The top phase containing the ester of fatty acid (biodiesel) was separated from the bottom phase (glycerol) using separating funnel. The excess methanol in the top phase was removed by distillation leaving behind the biodiesel according to the method described by Ndana and Manko (2010). The volume of the biodiesel and glycerol collected were measured and recorded. The process was repeated at 45 oC, 55 oC, 65 oC and 75 oC using equal volume of catalysed solution mixture (i.e. 400.00 cm<sup>3</sup> containing 10.00 cm<sup>3</sup> of 1M KOH.

#### Effect of Concentration of Catalyst (KOH) on Biodiesel Production

In order to investigate the effect of concentration of KOH (as a catalyst) on biodiesel production, 10.00 cm<sup>3</sup> each of 0.50 M, 1.00 M, 1.50 M, 2. 00 M and 2.50 M of KOH was added into 5 different reactors of equal capacity (i.e. 500.00 cm<sup>3</sup> round bottomed flasks) each containing 400.00 cm<sup>3</sup> of

the solution mixture earlier prepared, which were labeled A,B,C,D and E, respectively.

The catalysed solution mixtures in the reactors were heated at 65 oC along with stirring at the rate of 450 rpm using magnetic stirrer. The heating temperature, 65 oC was from the findings of the effect of temperature carried out earlier in the present work). The process of biodiesel collection was carried out as earlier described in the effect of temperature of the present work.

**Effect of Reaction Time on Biodiesel Production**

In this experiment, 10.00 cm<sup>3</sup> each of 1.00 M KOH was added into 5 different reactors of equal capacities (i.e. 500.00 cm<sup>3</sup> round bottomed flasks) each containing 400.00 cm<sup>3</sup> of solution mixture, which were labeled A, B, C, D and E.( The concentration of KOH used was from the findings of the effect of catalyst concentration in the preceding investigation in this work).

The catalysed solution mixtures were heated each at 65 oC along with stirring using magnetic stirrer at the rate of 450 rpm. The reaction times (minutes) used for transesterification reaction in A, B, C, D, and E were 35, 45, 55, 65, and 75, respectively. The process of biodiesel collection was carried out as previously described in the effect of temperature in this work.

**Determination of Saponification Value**

In order to determine the amount of soap generated as by-product due to side reactions of glycerol during transesterification of TGs into biodiesel, 25.00 cm<sup>3</sup> of glycerol obtained in each of the investigations (ie effects of temperature, concentration of catalyst and reaction time) carried out in the proceedings experiments was placed in a 250 ml conical flask containing 40.00 cm<sup>3</sup> of freshly prepared 0.10 M ethanolic potassium hydroxide solution. The conical flask was attached to a reflux condenser and heated at 65 oC on a water-bath for 30 minutes with frequent shaking to ensure the homogeneity of the solution mixture (i.e. glycerol and ethanolic potassium hydroxide solution). 1.00 cm<sup>3</sup> of 1% phenolphthalein indicator was added into the hot excess ethanolic potassium hydroxide solution and titrated with 0.10 M HCl. A blank titration was also carried out using distilled water. The process was repeated 3 times and the average titre volume of 0.10 M HCl used was computed. The saponification value was evaluated (in mol/dm<sup>3</sup>) using the modified form of equation adopted by Alabi (2014) below.

$$SV = \left( \frac{(S-B) \times C \times \text{mass of 0.1 M KOH}}{\text{Volume of glycerol used}} \right)$$

- where SV= Saponification Value
- S= Sample titre Value
- B= Blank titre value
- C= Molar concentration of HCl

**Results and Discussion**

**Results**

The results of all the experiments carried out in this work are shown in Tables 1-3 below. Table 1 shows the effect of temperature on transesterification of TGs into biodiesel and glycerol. Table 2 gives the results obtained under the effect of concentration of base catalyst (KOH) during the transesterification of TGs into biodiesel at 65 oC. Table 3 shows the effect of reaction time on transesterification of TGs into biodiesel and glycerol at 65 oC.

**Table 1: Effect of Temperature on Transesterification of 400.00 cm<sup>3</sup> of Solution Mixture Containing 10.00 cm<sup>3</sup> of 1.00 M KOH**

Temperature (°C)	35.00	45.00	55.00	65.00	75.00
Volume of biodiesel (cm <sup>3</sup> )	116.50	131.00	148.00	200.00	172.00
Volume of glycerol (cm <sup>3</sup> )	52.50	56.00	80.00	96.50	126.00
Saponification Value (mol/ dm <sup>3</sup> )	0.00	0.00	0.00	0.00	0.25

**Table 2: Effect of Concentration of Catalyst (KOH) on Transesterification of 400.00 cm<sup>3</sup> of Solution Mixture at 65°C**

Concentration of KOH (mol/ dm <sup>3</sup> )	0.50	1.00	1.50	2.00	2.50
Volume of biodiesel (cm <sup>3</sup> )	122.00	198.00	188.50	185.00	180.00
Volume of glycerol (cm <sup>3</sup> )	68.00	92.80	96.80	97.00	97.50
Saponification Value (mol/ dm <sup>3</sup> )	0.00	0.00	0.09	0.18	0.27

**Table 3: Effect of Reaction Time on Transesterification of 400.00 cm<sup>3</sup> of Solution Mixture Containing 10.00 cm<sup>3</sup> of 1.00 M KOH at 65°C**

Reaction time (minute)	35.00	45.00	55.00	65.00	75.00
Volume of biodiesel (cm <sup>3</sup> )	167.00	182.00	190.50	197.00	186.00
Volume of glycerol (cm <sup>3</sup> )	66.50	74.00	86.00	93.00	99.50
Saponification Value (mol/ dm <sup>3</sup> )	0.00	0.00	0.09	0.00	0.20

## Discussion

The result of the effect of temperature on transesterification reaction between *Gossipium hirsutum* oil and methanol is shown in Table 1. The result (Table 1) showed that transesterification reaction occurred within temperature range (35°C-75 °C), which significantly varied with temperature. The low yield of biodiesel and glycerol observed at temperatures below 65°C (i.e. 35°C, 45°C, 55°C) and the high yield of biodiesel and glycerol achieved at 65°C could be attributed to incomplete and complete transesterification reactions, respectively. This findings are in accordance with the findings of Garba et al (2012). The decrease in the amount of biodiesel and the corresponding increase in the amount of glycerol observed at 75°C may be attributed to the decomposition of biodiesel into glycerol as reported by Sensoz et al (2000). The little saponification value observed at 75°C could possibly be connected to side saponification reactions of TGs, which led to formation of soap (as by-product). This is also in accordance with the findings of Garba et al (2012).

Table 2. shows the influence of catalyst concentration on the amount of allied products (biodiesel and glycerol) and by-product (soap) generated through transesterification reaction between *Gossipium hirsutum* seed oil and methanol at 65°C. The result showed that 1.00 M was the optimum concentration of catalyst. The low yield observed at concentration (0.50 M) of catalyst and high yield recorded at concentration (1.00 M) of catalyst could be possibly be associated with the incomplete and complete conversions of TGs respectively as reported by Enciner et al (2005). The decrease in the amount of biodiesel and the corresponding increase in the amounts of glycerol and saponification values observed at concentrations above 1.00 M (ie 1.50 M, 2.00 M, and 2.50 M) of KOH may be associated with the over participation of more TGs in the saponification reaction with the KOH in the affecteds solution mixture as reported by Mohibbe and Waris Nahar (2005); Garba et al (2012).

Table 3 presents the result of the effect of reaction time on biodiesel and glycerol yield, as well, as the saponification

value recorded at 65°C. From the result (Table 3), it could be said that 65 minutes was the optimum reaction time for biodiesel production because it was the time at which highest collection of biodiesel was achieved. The increase in the volumes of biodiesel and glycerol at reaction times from 35 minutes to 65 minutes observed may be connected to progressive increase in transesterification reaction as reaction time increases to a maximum product yield at 65 minutes. This is because during transesterification, biodiesel production continues with the reaction time up to completion provided that there are enough reactants (oil and alcohol) in the reactor as reported by Sani et al (2014). The decrease in biodiesel and increase in glycerol noted at reaction time (75 minutes) may be associated with the hydrolysis of ester (the biodiesel formed). This is because after complete transesterification of TGs into biodiesel, extension of reaction time leads to hydrolysis of biodiesel formed into fatty acid, which causes the formation of more soap ( by-product) as reported by Garba et al (2012). The relative high saponification value obtained at reaction time (75 minute) could be connected to the formation of more soap from the hydrolysis of the ester formed into fatty acid. This is because fats and oils undergo hydrolysis with caustic alkali to form propane 1,2,3- triol and the corresponding sodium or potassium salts (soap) of the component fatty as reported by Ababio,(1985).

## Conclusion

Optimum operational conditions of temperature, reaction time and concentration of catalyst for maximum production of biodiesel from *Gossipium hirsutum* seed oil and methanol by base catalysed transesterification reaction were established. Therefore, the experimental findings of the present work could serve as basis for maximum production of environmentally-friendly biodiesel on large scale from renewable feedstocks (seed oils) as alternative to popular conventional environmentally-aggressive petrodiesel.

## Acknowledgements

The author sincerely acknowledged the contribution of Chemistry Department, University of Jos, Nigeria for the provision of chemicals and equipment.

## References

- Ababio, O. Y. (1985): New School Chemistry Certificate Science Series (Revised edition), Africana FEP Publishers Limited, in association with FEP International Private Limited, Hamzat Building, 22/26 Park Road, Sabongari, Zaria Pp. 495-499
- peruviana) Seed oil. Proceedings of 37th Annual International Conference, Workshop and Exhibition of Chemical Society of Nigeria (CSN), Vol. 2 Held at Ibom Hall, IBB Way, Uyo, Akwa Ibom State, Nigeria, Pp. 558-563
- Alabi, K. A. (2014): Chemical Characterization of Soluble Soap Prepared from Milkbush(*Theretia*
- Choundan, A. P. S. and Sarma, A. K. (2011): Modern Heterogeneous Catalyst for biodieselproduction;

- Comprehensive review. Renewable Sustainable Energy, 15: 4378-4399
- Ekwenchi, M. M. Akunwanne, B. U., Okeke, N. R. and Ekpenyong K. I. (1989): Gaseous fuel production by fungal degradation of elephant grass, Short Communication, Fuel, 69:1567-1572.
- Ewenchi, M. M. and Yaro, M. N. (2010): Gaseous fuel production by anaerobic fungal degradation of banana leaves. Chemsearch Journal, 1 (1): 28-32
- Enciner, J. M. Gonzalel, J. F. and Rodriquez, J. J. (2005): Vegetable oils transesterification of Cynara Cardunculus L. Oil and Ethanol Energy. Fuel, 16
- Garba, B. Gumel, S. M. and Babayo, M. B. (2012): Effects of Operational Parameter on Biodiesel Production. Dynamic in Science and Technology; publication of Kano University of Science and Technology, Wudil. Pp 11-20.
- Guo, F., Fang, Z., Xu, C. C. and Smith, R. L. (2012): Solid acid mediated hydrolysis of biomass for producing biofuel. Prog Energy Combustion Sci. 38: 672-690
- Mohibbe , A.M. and Waris-Naher, N. M. (2008): Prospects and Potentials of Fatty acid methyl ester of some non traditional seed oils for use as biodiesel in India. Boimas and Bioenergy, 29.
- Nasar, M., Taufiq, Y. H., Rashid, U and Lokman, T. B. (2012): Investigation of heterogeneous solid acid catalyst performance on low grade feedstocks for biodiesel production; A review, ELSEVIER:Energy conservation Management. (In press)
- Ndana, M. and Manko, M. U (2010): Biodiesel Production: A future energy Option for auromobiles and power generating plants in Nigeria. Kontagora Journal of Science and Technology, 8(1)Nusterer, E. Biochi, P. E and Schuwarz, K.(1996): Interaction of water and methanol with a zeolite at high coverages Chemical Physics Lett., 253:448-455
- Pinto, A. C., Guariero, L. L. N., Rezende, M. J. C., Rineiro, N., M., Torres, E. A. and Lopes, W. A. (2005): An overview, Brazil Chemical Society, 13: 13-30.
- Sani, Y. M. Wan, D. W. and Abdulaziz, A. R. (2014):Activity of Solid acid catalyst for biodiesel production, a critical review Applied Catalyst A; 470: 140-161
- Shajaratun, N. Z. A., Taufiq-Yap, Y.H, Rabiah , N. M. F., (2014): A production of Biodiesel from Palm Oil using modified Malaysian natural Dolomites,ELSEVIER:Energy Conser and Management,78:738-744
- Sensoz, S. Angin, D. and Yargin, S. (2000): Influence of particle size on the pyrolysis of repeseed (Barassica napus L fuel properties of bio-oil. Biomass and Bioenergy ,19: 271-279.

## Author's Profile



Dr. M. N. Yaro was born at Dawakin-Tofa town, Dawakin-Tofa L.G.A., Kano State-Nigeria on the 26th December, 1971. He attended Central Primary School D/Tofa from 1976 - 1981; G.S.S. D/Tofa from 1981 to 1986; Advanced Teachers' College, Gumel, where he Obtained NCE (Chemistry / Physics) in 1989; Usmanu Danfodiyo University, Sokoto-Nigeria, where he obtained BSc. and MSc Degrees in Applied Chemistry in 1994 and 2004, respectively and; University of Jos-Nigeria from 2004 to 2010, where he obtained Ph.D in Applied Physical Chemistry in February, 2011. Dr. Yaro also attended a

Renewable Energy and Environmental Chemistry. Dr. Yaro is a registered members of the: Institute of Chartered Chemistry of Nigeria (ICON), Chemical Society of Nigeria (CSN) and Teachers' Registration Council of Nigeria (TRCN). Dr. Yaro worked with Kano State Ministry of Education (As a teacher) from 1989 - 2001 and Federal College of Education (Technical), Bichi from 2002 - 2012 (as Chemistry Lecturer ). Dr. Yaro is Currently an Associate Professor in the Department of Chemistry of the Federal University, Dutse, Jigawa-Nigeria.

IJSER

computer training course at Kano State College of Education from June 2004 - September 2004, where he obtained a Certificate in Computer Application and Data Processing. The area of research interest of Dr. Yaro is