

To study Advance Construction Material Micro Silica in Concrete

Nikhil bhatt¹, Dr.Sanjeev Gill²

Assit Prof. Department of Civil Engineering, JBIT, Dehradun(U.K)
HOD Civil Engineering Department, JBIT, Dehradun (U.K)

Abstract: Micro silica is an amorphous type of silica dust mostly collected in bag house filters as by-product of the silicon and ferro-silicon production. The paper summarizes important physical and chemical properties of micro silica and uses those results for an evaluation of micro silica from a Health Safety and Environment (HSE) standpoint. Micro silica consists of spherical particles with an average particle size of 150 nm and a specific surface area of typically 20 m²/g. The chemical and physical properties of this inorganic product are different as compared to other amorphous and crystalline silica poly morphs. More than 500.000 MT of micro silica are sold to the building industry world-wide and are used in fibre cement, concrete, oil-well drilling, refractories, and even in polymers. Micro silica contains trace amounts of heavy metal oxides and organic deposits, which originate from natural raw materials. Since the concentration of these impurities is very low, micro silica complies with company and international.

Keywords- micro silica, concrete, compressive strength, fibre, admixture

1 INTRODUCTION

Micro silica is a mineral admixture composed of very fine solid glassy spheres of silicon dioxide (SiO₂). Most micro silica particles are less than 1 micron (0.00004 inch) in diameter, generally 50 to 100 times finer than average cement or fly ash particles. Frequently called condensed silica fume, micro silica is a byproduct of the industrial manufacture of ferrosilicon and metallic silicon in high-temperature electric arc furnaces. The ferrosilicon or silicon product is drawn off as a liquid from the bottom of the furnace. Vapor rising from the 2000-degree-C furnace bed is oxidized, and as it cools condenses into particles which are trapped in huge cloth bags. Processing the condensed fume to remove impurities and control particle size yields micro silica. Micro silica, also known as Silica fume is fine amorphous silica. Added to concrete at around 30kg/m³ it changes the rheology and reacts with the cement hydration products to dramatically improve concrete strengths, durability and impermeability, allowing concrete to be used in ways never before possible. When pozzolanic materials are incorporated to concrete, the silica present in these materials react with the calcium hydroxide released during the hydration of cement and forms additional calcium silicate hydrate (C – S – H), which improve durability and the mechanical properties of concrete. High strength concrete refers to concrete that has a uniaxial compressive strength greater than the normal strength concrete obtained in a particular region. High strength and high performance concrete are being widely used throughout the world and to produce them, it is necessary to reduce the water binder ratio and increase the binder content. High strength concrete means good abrasion, impact and cavitations resistance. Using high strength concrete in structures today would result in economical advantages. In future, high range

water reducing admixtures (Super plasticizer) will open up new possibilities for use of these materials as a part of cementing materials in concrete to produce very high strengths, as some of them are make finer than cement.

Fig.1 Micro silica is 100 x finer than cement and the particles are spherical. 1.2 Aids strength gain of fly ash concretes: Preliminary indications suggest that micro silica may be useful in controlling heat generation in mass concrete. It has also been found useful in combination with fly ash. Early-age strength development of concrete in which fly ash replaces cement tends to be slow because fly ash is relatively inert during this period of hydration. Adding micro silica, which is more reactive in early hydration, can speed the strength development. 0 Methodology The methodology adopted comprised of both preliminary and experimental investigations carried out using the study material and these are presented as follows:

1.1 Preliminary Investigations

For the preliminary investigations, micro silica and cement was subjected to physical and chemical analyses to determine whether they are in compliance with the standard used. The experimental program was designed to investigate silica fume as partial cement replacement in concrete. The replacement levels of cement by silica fume are selected as 5%, 10%, 15%, 20%, and 25% for standard size of cubes for the M30 grade of concrete. The specimens of standard cubes (150 x 150 x 150 mm), was casted with silica fume. Compressive machine was used to test all the specimens. The specimens were casted with M30 grade concrete with different replacement levels of cement from 0 to 25% with silica

fume. Seventy two samples was casted and the cubes were put in curing tank for 3, 7, 14, and 28 days and density of the cube, and compressive strength were determined and recorded down accordingly. The other materials used are listed as follow: Cement Ordinary Portland cement produced by QNCC was used in this study. The cement conformed to the requirements of BS 12 (1996).

1.1.1 Aggregates

There are the inert filler in the concrete mixture which constitute between 70 – 75% by volume of the whole mixture. The sand used was collected within Ibadan metropolis, Nigeria. It was clean and free from organic material and clay. The coarse aggregate used were mainly material retained on a 4.7mm BS 410 test sieve and contained only so much fine materials as was permitted for various sizes in the specification.

1.1.2 Water

The water used for the study was free of acids, organic matter, suspended solids, alkalis and impurities which when present may have adverse effect on the strength of concrete. Mixing And Placing Considerations Handling the micro silica Because of its extreme fineness, micro silica presents handling problems. A cement tanker that could ordinarily haul 35 metric tons of cement accommodates only 7 to 9 tons of dry micro silica and requires 20 to 50 percent more time for discharging. Some producers mix micro silica with water on a pound-for-pound basis ton form a slurry that is transportable in tank trailers designed to handle liquids.



T

Table 1 : Mix proportion for 30Mpa

Materials	Mix Proportion (Kg)					
	Cement	MS 5%	MS 10%	MS 15%	MS 20%	MS 25%
Cement (Kg)	370.0	351.5	333.0	314.5	296.0	277.5
Micro silica (Kg)	0	18.5	37.0	55.5	74.0	92.5
Total Water	140	140	140	140	140	140

The water of the slurry replaces part of that ordinarily added to the mix. One supplier prepares a slurry which, used at the rate of 1 gallon per 100 pounds of cement, will provide about 5 percent micro silica by weight of cement. In 1984, that supplier was quoting a price of \$1.70 per gallon at a plant in West Virginia. In Canada, patented methods have been used to densify the micro silica for shipment to ready mix producers. Some concrete producers also use the loose micro silica just as it is collected. Water requirements of the mix. When no water reducing agent is used, the addition of micro silica to a concrete mix calls for more water to maintain a given slump. Water content can be held the same by using a water reducer or super plasticizer along with the micro silica. Water reducing agents appear to have a greater effect on micro silica concrete than on normal concrete. Thus water demand for given micro silica concrete can be controlled to be either greater or smaller than for the reference concrete. Placing and finishing, curing The gel that forms during the first minutes of mixing micro silica concrete takes up water and stiffens the mixture, necessitating adjustment of the timing of charging and placing. Scandinavian researchers have concluded that micro silica concretes often require 1 to 2 inches more slump than conventional concrete for equal workability. When cement content and micro silica dosage are relatively high, the mixture is so cohesive that there is virtually no segregation of aggregates and little bleeding. This may cause problems for floors or slabs

Ltr)						
Fine Aggregate (Kg)	780	780	780	780	780	780
Coarse Aggregate (Kg)	1180	1180	1180	1180	1180	1180
MS432 (ltr)	4	4	4	4	4	4
W/C	0.38	0.38	0.38	0.38	0.38	0.38

2 TESTING OF SPECIMENS

Compressive strength test were carried out at specified ages on the cubes. The consisted of the application of uniaxial compressive load on the cube until failure at which point the load require for failure of each cube was noted, prior to testing, the density of each cube was determined using standard procedures for density determinations.

for varying Micro Silica Replacement Levels in
concrete Compressive Strength of Concrete Discussions



compression Testing machine

2.1 Compressive Strength of Concrete

The test was carried out conforming to BS EN:12390 – 3: 2009 to obtain compressive strength of M30 grade of concrete. The compressive strength of high strength concrete with OPC and silica fume concrete at the age of 3, 7, 14 and 28 days are presented in table 3.5. here is a significant improvement in the strength of concrete because of the high pozzolanic nature of the micro silica and its void filling ability. The compressive strength of the mix M30 at 3, 7, 14 and 28 days age, with replacement of cement by micro silica was increased gradually up to an optimum replacement level of 10% and then decreased. The maximum 3, 7, 14 and 28 days cube compressive strength of M30 grade with 10% of silica fume was 30.35, 38.26, 44.51, and 48.22 mpa respectively. The compressive strength of M30 grade concrete with partial replacement of 10% cement by silica fume shows 15.31% greater than the controlled concrete. The maximum compressive strength of concrete with silica fume depends on three parameters, namely the replacement level, water cement ratio and chemical admixture. The super plasticizer admixture dosage plays a vital role in concrete to achieve the 0% to 25% there is a decrease in compressive strength for 3, 7, 14 and 28 days curing period. It was observed that the percentage of micro silica are given workability at lower w/c ratio. Cement replacement up to 10% with micro silica leads to increase in compressive strength and beyond replacement from average concrete strength (mpa) in table 3.3 were 16.15%, 29.24%, 23.98% and 20.22% for 3, 7, 14 and 28 days. The percentage given above shown that the compressive strength increased from 3 days to 7 days and decreased from 14 days to 28 days i.e. (23.98% to 20.22%). The maximum replacement level of silica fume is 10% for M30 grade. Table 2 : Compressive strength Test Result

%MS Replacement	Compressive Strength of Concrete(Mpa)			
0	26.32	30.55	36.07	40.55
5	28.11	33.11	40.77	44.44
10	30.67	38.26	44.72	48.75
15	29.19	34.59	42.58	45.17
20	28.02	31.40	36.25	41.53

Micro silica in concrete contributes to strength and durability two ways:

20.1 Pozzolanic effect:

When water is added to OPC hydration occurs forming two products, as shown below: OPC + H₂O CSH (Calcium silicate hydrate) + Ca(OH)₂ the presence of micro silica the silicon dioxide from the micro silica will react with the calcium hydroxide to produce more aggregate binding CSH as follows:-Ca(OH)₂ + SiO₂ + H₂O CSH The reaction reduces the amount of calcium hydroxide in the concrete. The weaker calcium hydroxide does not contribute to strength. When combine with carbon dioxide, it forms a soluble salt

specifications for the material or its applications. Dosages of micro silica used in concrete have typically been in the range of 5 to 20 percent by weight of cement, but percentages as high as 40 have been reported.

Tabl Chemical and Physical Composition

	U Unit	OPC	Fly ash	Micro silica
SiO ₂	%	17 – 25	40 – 55	90 – 98
CaO	%	60 – 67	1 – 5	0.2 – 0.7
Al ₂ O ₃	%	2 – 8	20 – 30	0.4 – 0.9
Fe ₂ O ₃	%	0 – 6	5 – 10	1 – 2
Other	%	1 – 8	4 -15	2 – 3
S. G	Kg/m ³	3150	2100	2200
Bulk density	Kg/m ³	1400	900 – 1000	550 – 650
Surface Area	m ² /kg	200 -500	200 – 600	20,000

2.1.2 How microsilica improves concrete

Finer than fly ash, this pozzolana increases strength and density, reduces concrete permeability Since micro silica particles are only about 1/100 the size of cement grains, the material may be hard to batch and ship. These handling problems may be overcome by mixing micro silica with water (and sometimes other admixtures) in a slurry which replaces part of the normal concrete mixing water. Densification and pelletization have also been tried to simplify the mixing and handling. Figure 4.Flowchart of Microsilica (improving concrete) Micro silica Concrete Applications. Because of the pozzolanic and micro filler effect of micro silica, its use in concrete can improve many of its properties opening up a wide range of applications including.

3 CORROSIONRESISTANCE

The reduced permeability of micro silica provides protection against intrusion of chloride ions there by increasing the time taken for the chloride ions to reach the steel bar and initiate corrosion. In addition, micro silica concrete has much higher electrical resistivity compared to OPC concrete thus slowing down the corrosion rate. The combined effect generally increased structures life by 5 – 10 times. Micro silica concrete is

therefore suitable for structures exposed to salt water, de-icing salts, ie. Harbor structures, ports, bridges, docks, on shores constructions situated in areas with chlorides in the ground water, soil and in the air.

4 SULPHATE RESISTANCE

Micro silica concrete has a low penetrability and high chemical resistance that provides a higher degree of protection against sulphates than low C3A sulphate resisting cements or other cementitious binder systems.

5 HEAT REDUCTION

By replacing cement with Micro silica and observing the efficiency factor of Micro silica, a lower maximum temperature rise and temperature differential will take place for concrete with the same strength. It performs better than slag andfly-ash blends in thick sections. It is also the most effective way of achieving low heat without sacrificing early age strength. Silica Fume WaterproofConcrete Because of its low permeability, micro silica can be use as an integral water proofer for below ground structures where some dampness is acceptable, eg. carparks High Strength Concrete: Micro silica in conjunction with superplasticizers is used to produce very high strength concrete (70 – 120 MPa). High strength concretes provides large economic benefits to developers e.g. reduced column and wall thickness in tall buildings and improved construction schedule. It is also much more easier to pump micro silica concrete up the highrise buildings during construction.Shotcrete Micro silica is use in shotcrete whether produced by wet or dry process to reduce the rebound, to increase application thickness per pass, improve resistance to wash out in marine construction or wet areas and to improve the properties of hardened shotcrete. With fibres it can eliminate mesh and reduce cracking.

6 ABRASIONRESISTANCE

Microsilica concrete has very high abrasion resistance. In floor and pavement construction it's use saves money

and time and improves operational efficiencies for the facility operator. It also improves the hydraulic abrasion-erosion resistance of concrete thus making it suitable for use in dam spillways.

7 CHEMICAL RESISTANCE:

Microsilica concrete is widely used in industrial structures exposed to an array of chemicals aggressive. In the alimentary industry the exposure comes from fat acids and other acids, detergents, etc. In the chemical industry there is exposure from.

8 CONCLUSIONS

1. Cement replacement up to 10% with silica fume leads to increase in compressive strength, for M30 grade of concrete. From 15% there is a decrease in compressive strength for 3, 7, 14 and 28 days curing period.
2. It was observed that the compressive strength of M30 grade of concrete is increased from 16.15% to 29.24% and decrease from 23.98% to 20.22%.
3. The maximum replacement level of silica fume is 10% for M30 grade of concrete.

4. The use of micro silica in high strength concrete leads to economical and faster construction.

5. Due to use of the micro silica in a OPC concrete the life of that concrete is increase 4-5 times than the OPC concrete.

9 REFERENCES

- [1] International journal of civil and structural engineering. Volume 2, No 1, 2011 © Copyright 2010 All rights reserved Integrated Publishing services Research article ISSN 0976 – 4399-Effect of replacement of Cement by Micro silica 600 on the properties of Waste Plastic Fibre Reinforced (WPFRC) Concrete – An experimental investigation-by Prahallada M. C1, Prakash K.B2.
- [2] IOSR Journal of Mechanical and Civil Engineering (IOSR-JMCE) e-ISSN: 2278-1684,p-ISSN: 2320-334X, Volume 6, Issue [3] (May. – Jun. 2013), PP 57-63 www.iosrjournals.org www.iosrjournals.org 57 | Page Experimental -Investigations of Mechanical properties on Micro silica (Silica Fume) and Fly Ash as Partial Cement Replacement of High Performance Concrete – by-Magudeaswaran P1, Eswaramoorthi P2.
- [4] International Journal of Emerging Technology and Advanced Engineering Website: www.ijetae.com (ISSN 2250-2459, Volume 2, Issue 8, August 2012).- Effect of Partial Replacement of Cement by Silica

IJSER