

# Variation of OPC-Rice Husk Ash-Saw Dust Ash Composites Strength under Prolonged Curing

L. O. Ettu<sup>1</sup>, U. C. Anya<sup>2</sup>, K. C. Nwachukwu<sup>3</sup>, J. I. Arimanwa<sup>4</sup>, and H. E. Opara<sup>5</sup>

<sup>1,2,3,4</sup>Department of Civil Engineering, Federal University of Technology, Owerri, Nigeria.

<sup>5</sup>Department of Civil Engineering, Imo State University, Owerri, Nigeria.

**Abstract**— This work investigated the variation of OPC-Rice Husk Ash (RHA)-Saw Dust Ash (SDA) composites strength under prolonged curing. 165 concrete cubes, 165 sandcrete cubes, and 165 soilcrete cubes of 150mm x 150mm x 150mm were produced at percentage OPC replacement with RHA-SDA of 0% (control), 5%, 10%, 15%, and 20% and crushed to obtain their compressive strengths at 3, 7, 14, 21, 28, 50, 90, 120, 150, 180, and 210 days of curing. The compressive strength values of the OPC-RHA-SDA ternary blended cement composites at all percentage replacement of OPC with RHA-SDA were much lower than the control values at 3-21 days. For concrete, the control strength values rose to 23.50N/mm<sup>2</sup> at 28 days and 30.50N/mm<sup>2</sup> at 210 days. The strength values for 10% and 15% replacement of OPC with RHA-SDA were respectively 22.50N/mm<sup>2</sup> and 20.80N/mm<sup>2</sup> at 28 days and 31.50N/mm<sup>2</sup> and 30.60N/mm<sup>2</sup> at 210 days. Thus, whereas the control concrete attained 130% of its 28-day strength at 210 days, 10% OPC replacement with RHA-SDA attained 140% of its 28-day strength at 210 days and 15% OPC replacement with RHA-SDA attained 147% of its 28-day strength at 210 days. Sandcrete and soilcrete strength variations were similar to but more pronounced than that of concrete. The continued more rapid increase in strength of OPC-RHA-SDA composites compared to purely OPC composites between 28 and 210 days suggests that OPC-RHA-SDA ternary blended cement structural members could be designed using some suitably higher strength values than the 28-day strength if they would not be fully loaded for some reasonable period after construction.

**Index Terms**— Blended cement, composites, concrete, prolonged curing, rice husk ash, sandcrete, saw dust ash, soilcrete.

## 1 INTRODUCTION

Researchers have greatly intensified efforts at sourcing local materials that could be used as partial replacement for Ordinary Portland Cement (OPC) in civil engineering and building works. Supplementary cementitious materials have been proven to be effective in meeting most of the requirements of durable concrete such that blended cements are now used in many parts of the world [1]. Calcium hydroxide [Ca(OH)<sub>2</sub>] is obtained as one of the hydration products of OPC. When blended with Portland cement, a pozzolanic material reacts with the Ca(OH)<sub>2</sub> to produce additional calcium-silicate-hydrate (C-S-H), which is the main cementing component. Therefore, the pozzolanic material serves to reduce the quantity of the deleterious Ca(OH)<sub>2</sub> and increase the quantity of the beneficial C-S-H. Dwivedia et al. [2] report that the cementing quality is enhanced if a good pozzolanic material is blended in suitable quantity with OPC

Industrial waste pozzolans such as fly ash (FA) and silica fume (SF) are already widely used in many countries [3]. Attempts are also being made to produce and use pozzolanic agricultural by-product ashes such as rice husk ash (RHA) and saw dust ash (SDA) commercially in some countries. Malhotra and Mehta [4] found that ground RHA with finer particle size than OPC improves concrete properties, including that higher substitution amounts results in lower water absorption values and the addition of RHA causes an increment in the compressive strength. Sakr [5] investigated the effects of silica fume (SF) and RHA on the properties of heavy weight concrete and found that these pozzolans gave higher concrete strengths

than OPC concrete at curing ages of 28 days and above. Agbede and Obam [6] investigated the strength properties of OPC-RHA blended sandcrete blocks. They replaced various percentages of OPC with RHA and found that up to 17.5% of OPC can be replaced with RHA to produce good quality sandcrete blocks. Wada et al. (2000) demonstrated that RHA mortar and concrete exhibited higher compressive strength than the control mortar and concrete. Rukzon and Chindaprasirt [7] investigated the strength development of mortars made with ternary blends of OPC, ground RHA, and classified fly ash (FA). The results showed that the strength at the age of 28 and 90 days of the binary blended cement mortar containing 10 and 20% RHA were slightly higher than those of the control, but less than those of FA. The researchers concluded that 30% of OPC could be replaced with the combined FA and RHA pozzolan without significantly lowering the strength of the mixes.

Mehta and Pirtz [8] investigated the use of RHA to reduce temperature in high strength mass concrete and found that RHA is very effective in reducing the temperature of mass concrete compared to OPC concrete. Fadzil et al. [9] studied the properties of ternary blended cementitious (TBC) systems containing OPC, ground Malaysian RHA, and FA. They found that at long-term period, the compressive strength of TBC concrete was comparable to the control mixes even at OPC replacement of up to 40% with the pozzolanic materials. Cordeiro, Filho, and Fairbairn [10] carried elaborate studies of RHA and rice straw ash (RSA) and demonstrated that grind-

ing increases the pozzolanicity of RHA and that high strength of RHA, RSA concrete makes production of blocks with good bearing strength in a rural setting possible. Their study showed that combination of RHA or RSA with lime produces a weak cementitious material which could however be used to stabilize laterite and improve the bearing strength of the material. Elinwa, Ejeh, and Akpabio [11] found that sawdust ash can be used in combination with metakaolin as a ternary blend with 3% added to act as an admixture in concrete. Elinwa, Ejeh, and Mamuda [12] and Elinwa and Abdulkadir [13] have also investigated the suitability of sawdust ash as a pozzolanic material and found that it could be used in binary combination with OPC to improve the properties of cement composites.

Recent studies by Ettu et al. [14], Ettu et al. [15], Ettu et al. [16], and Ettu et al. [17] have confirmed the suitability of Nigerian RHA and SDA as pozzolanic materials for producing concrete, sandcrete, or soilcrete. What remains is to investigate the effects of some key factors on the strengths of OPC-RHA-SDA ternary blended cement composites. The effect of curing age on the strength of purely OPC composites is well known. For example, so long as the hydration of anhydrous cement particles goes on, concrete strength increases with increase in the moist curing period [18]. This is so because the strength of concrete depends on the amount of gel (the C-S-H which is the essential cementing compound) in the cement paste at any time, and this itself is a function of curing age. The amount of gel produced at any given time also depends on the type of cement because different cements require a different length of time to produce the same quantity of gel [19]. Thus, this work investigated the variation of strength of OPC-RHA-SDA ternary blended cement composites under prolonged curing. The knowledge of this variation would be of great importance when a structure is to be subjected to full loading at a later age in which case the gain in the strength after the age of 28 days could be taken into account in design.

## 2 METHODOLOGY

Rice husk was obtained from rice milling factories in Afikpo, Ebonyi State and Saw dust from wood mills in Owerri, Imo State, all in South Eastern Nigeria. These materials were air-dried and calcined into ashes in a locally fabricated furnace at temperatures generally below 650°C. The rice husk ash (RHA) and sawdust ash (SDA) were sieved and large particles retained on the 600µm sieve were discarded while those passing the sieve were used for this work. No grinding or any special treatment to improve the quality of the ashes and enhance their pozzolanicity was applied because the researchers wanted to utilize simple processes that could be easily replicated by local community dwellers.

The RHA had a bulk density of 770 Kg/m<sup>3</sup>, specific gravity of 1.85, and fineness modulus of 1.45. The SDA had a

bulk density of 820 Kg/m<sup>3</sup>, specific gravity of 2.05, and fineness modulus of 1.89. Other materials used for the work are Ibeto brand of Ordinary Portland Cement (OPC) with a bulk density of 1650 Kg/m<sup>3</sup> and specific gravity of 3.13; river sand free from debris and organic materials with a bulk density of 1590 Kg/m<sup>3</sup>, specific gravity of 2.80, and fineness modulus of 2.90; crushed granite of 20 mm nominal size free from impurities with a bulk density of 1550 Kg/m<sup>3</sup>, specific gravity of 3.00, and fineness modulus of 3.70; laterite free from debris and organic materials with a bulk density of 1470 Kg/m<sup>3</sup>, specific gravity of 2.40, and fineness modulus of 3.35; and water free from organic impurities.

A simple form of pozzolanicity test was carried out for each of the ashes. It consists of mixing a given mass of the ash with a given volume of Calcium hydroxide solution [Ca(OH)<sub>2</sub>] of known concentration and titrating samples of the mixture against H<sub>2</sub>SO<sub>4</sub> solution of known concentration at time intervals of 30, 60, 90, and 120 minutes using Methyl Orange as indicator at normal temperature. For each of the ashes the titre value was observed to reduce with time, confirming the ash as a pozzolan that fixed more and more of the calcium hydroxide, thereby reducing the alkalinity of the mixture. The chemical analysis of the ashes showed they both satisfied the ASTM requirement that the sum of SiO<sub>2</sub>, Al<sub>2</sub>O<sub>3</sub>, and Fe<sub>2</sub>O<sub>3</sub> should be not less than 70% for pozzolans.

A standard mix ratio of 1:2:4 (blended cement: sand: granite) was used for concrete, 1:6 (blended cement: sand) for sandcrete, and 1:6 (blended cement: laterite) for soilcrete. Batching was by weight and a constant water/cement ratio of 0.6 was used. Mixing was done manually on a smooth concrete pavement. The RHA and SDA were first blended in equal proportions and subsequently blended with OPC at the required proportions before mixing with the fine aggregate-coarse aggregate mix (or fine aggregate only for sandcrete and soilcrete), also at the required proportions. Water was then added gradually and the entire concrete, sandcrete, or soilcrete heap was mixed thoroughly to ensure homogeneity. One hundred and sixty-five (165) granite concrete cubes, one hundred and sixty-five (165) sandcrete cubes, and one hundred and sixty-five (165) soilcrete cubes of 150mm x 150mm x 150mm were produced at percentage OPC replacement with RHA-SDA of 0% (control), 5%, 10%, 15%, and 20%. All the concrete cubes were cured by immersion while the sandcrete and soilcrete cubes were cured by water sprinkling twice daily in a shed. Three concrete cubes, three sandcrete cubes, and three soilcrete cubes for each percentage replacement of OPC with RHA-SDA were tested for saturated surface dry bulk density and crushed to obtain their compressive strengths at 3, 7, 14, 21, 28, 50, 90, 120, 150, 180, and 210 days of curing.

## 3 RESULTS AND DISCUSSION

The particle size analysis showed that both the RHA

and the SDA were much coarser than OPC, the reason being that the ashes were not ground to finer particles. Therefore, the compressive strength values obtained using them can still be improved upon when the ashes are ground to finer particles. The pozzolanicity test confirmed both ashes as pozzolans since they fixed some quantities of lime over time. The variation of the compressive strengths of the OPC-RHA-SDA ternary blended cement composites under prolonged curing is shown in Tables 1, 2, and 3 for concrete, sandcrete, and soilcrete respectively.

**TABLE 1**  
**COMPRESSIVE STRENGTH OF OPC-RHA-SDA CEMENT CONCRETE**

Age (days)	Compressive Strength (N/mm <sup>2</sup> ) for				
	0 % RHA/SDA	5 % RHA/SDA	10 % RHA/SDA	15 % RHA/SDA	20 % RHA/SDA
3	8.20	5.30	4.90	4.40	3.80
7	14.30	9.80	9.40	8.20	7.80
14	21.90	18.00	17.90	15.70	14.00
21	22.50	21.40	20.90	19.00	17.00
28	23.50	24.80	22.50	20.80	18.80
50	25.80	26.20	24.70	23.80	22.00
90	27.40	28.70	27.80	26.20	24.30
120	28.20	30.00	29.00	27.80	26.70
150	29.30	30.50	29.60	29.00	28.80
180	30.00	30.80	30.10	29.50	29.00
210	30.50	31.10	31.50	30.60	29.70

**TABLE 2**  
**COMPRESSIVE STRENGTH OF OPC-RHA-SDA CEMENT SANDCRETE**

Age (days)	Compressive Strength (N/mm <sup>2</sup> ) for				
	0 % RHA/SDA	5 % RHA/SDA	10 % RHA/SDA	15 % RHA/SDA	20 % RHA/SDA
3	2.90	2.00	2.00	1.80	1.60
7	5.20	3.10	3.00	2.50	2.40
14	7.40	4.40	4.20	3.70	3.30
21	8.30	5.30	5.00	4.70	4.00
28	9.70	7.90	7.40	6.60	5.70
50	10.60	10.00	9.70	9.00	8.40
90	11.30	11.50	11.30	10.80	10.00
120	11.60	12.00	11.80	11.30	10.40
150	12.10	12.40	12.50	12.00	11.20
180	12.40	12.80	13.00	12.50	11.70
210	12.60	13.00	13.30	12.80	12.10

**TABLE 3**  
**COMPRESSIVE STRENGTH OF OPC-RHA-SDA CEMENT SOILCRETE**

Age (days)	Compressive Strength (N/mm <sup>2</sup> ) for				
	0 % RHA/SDA	5 % RHA/SDA	10 % RHA/SDA	15 % RHA/SDA	20 % RHA/SDA
3	2.80	2.00	1.80	1.50	1.50
7	4.20	3.00	2.80	2.60	2.40
14	6.00	4.40	4.00	3.50	3.20
21	6.60	5.10	5.00	4.00	3.80
28	8.40	7.30	7.00	6.50	5.50
50	9.20	9.00	8.90	8.60	8.30
90	9.80	10.10	10.00	9.90	9.50
120	10.00	10.50	10.70	10.30	9.90
150	10.50	11.00	11.40	11.10	10.40
180	10.70	11.50	12.00	11.20	10.80
210	10.90	12.00	12.40	11.80	11.00

It can be seen from Tables 1, 2, and 3 that the compressive strength values of the OPC-RHA-SDA ternary blended cement composites at all percentage replacement of OPC with RHA-SDA were much lower than the control values at 3-21 days, but increased to become comparable to and even greater than the control values at some later days of curing. This consistent pattern for all the composites has been explained by Ettu et al. (2013e) and Ettu et al. (2013f) as being a result of the low rate of pozzolanic reaction at those early ages. The silica from the pozzolans reacts with lime produced as by-product of hydration of OPC to form additional calcium-silicate-hydrate (C-S-H) that increases the binder efficiency and the corresponding strength values at later days of curing.

For concrete, the control strength values rose to 23.50N/mm<sup>2</sup> at 28 days, 28.20N/mm<sup>2</sup> at 120 days, and 30.50N/mm<sup>2</sup> at 210 days. The strength values for 10% and 15% replacement of OPC with RHA-SDA were respectively 22.50N/mm<sup>2</sup> and 20.80N/mm<sup>2</sup> at 28 days, 29.00N/mm<sup>2</sup> and 27.80N/mm<sup>2</sup> at 120 days, and 31.50N/mm<sup>2</sup> and 30.60N/mm<sup>2</sup> at 210 days. Thus, whereas the control attained 120% and 130% of its 28-day strength at 120 and 210 days respectively, 10% OPC replacement with RHA-SDA attained 129% and 140% of its 28-day strength at 120 and 210 days respectively, and 15% OPC replacement with RHA-SDA attained 134% and 147% of its 28-day strength at 120 and 210 days respectively.

For sandcrete, the control strength values rose to 9.70N/mm<sup>2</sup> at 28 days, 11.60N/mm<sup>2</sup> at 120 days, and 12.60N/mm<sup>2</sup> at 210 days. The strength values for 10% and 15% replacement of OPC with RHA-SDA were respectively 7.40N/mm<sup>2</sup> and 6.60N/mm<sup>2</sup> at 28 days, 11.80N/mm<sup>2</sup> and 11.30N/mm<sup>2</sup> at 120 days, and 13.30N/mm<sup>2</sup> and 12.80N/mm<sup>2</sup> at 210 days. Thus, whereas the control attained 120% and 130% of its 28-day strength at 120 and 210 days respectively, 10%

OPC replacement with RHA-SDA attained 159% and 180% of its 28-day strength at 120 and 210 days respectively, and 15% OPC replacement with RHA-SDA attained 171% and 194% of its 28-day strength at 120 and 210 days respectively.

For soilcrete, the control strength values rose to 8.40N/mm<sup>2</sup> at 28 days, 10.00N/mm<sup>2</sup> at 120 days, and 10.90N/mm<sup>2</sup> at 210 days. The strength values for 10% and 15% replacement of OPC with RHA-SDA were respectively 7.00N/mm<sup>2</sup> and 6.50N/mm<sup>2</sup> at 28 days, 10.70N/mm<sup>2</sup> and 10.30N/mm<sup>2</sup> at 120 days, and 12.40N/mm<sup>2</sup> and 11.80N/mm<sup>2</sup> at 210 days. Thus, whereas the control attained 119% and 130% of its 28-day strength at 120 and 210 days respectively, 10% OPC replacement with RHA-SDA attained 153% and 177% of its 28-day strength at 120 and 210 days respectively, and 15% OPC replacement with RHA-SDA attained 158% and 182% of its 28-day strength at 120 and 210 days respectively.

These results indicate that the variation of strength of OPC-RHA-SDA ternary blended cement composites under prolonged curing is different from that of purely OPC composites (with 0% RHA-SDA) and depends on the percentage OPC replacement with RHA-SDA. The continued more rapid increase in strength of OPC-RHA-SDA composites compared to purely OPC composites between 28 and 210 days also suggests that some pozzolanic activity could still be going on at such later curing ages. This observation is particularly useful in that designers of structures that would not be fully loaded until some months after construction could use more suitable design strengths of OPC-RHA-SDA ternary blended cement composites higher than those attainable at 28 days of curing.

#### 4 CONCLUSIONS

- i. The compressive strength values of the OPC-RHA-SDA blended cement composites at all percentage replacement of OPC with RHA-SDA were much lower than the control values at 3-21 days, but increased to become comparable to and even greater than the control values at some later days of curing.
- ii. Whereas the control concrete attained 120% and 130% of its 28-day strength at 120 and 210 days respectively, 10% OPC replacement with RHA-SDA attained 129% and 140% of its 28-day strength at 120 and 210 days respectively, and 15% OPC replacement with RHA-SDA attained 134% and 147% of its 28-day strength at 120 and 210 days respectively.
- iii. Similarly, whereas the control sandcrete attained 120% and 130% of its 28-day strength at 120 and 210 days respectively, 10% OPC replacement with RHA-SDA attained 159% and 180% of its 28-day strength at 120 and 210 days respectively, and

15% OPC replacement with RHA-SDA attained 171% and 194% of its 28-day strength at 120 and 210 days respectively.

- iv. In like pattern, whereas the control soilcrete attained 119% and 130% of its 28-day strength at 120 and 210 days respectively, 10% OPC replacement with RHA-SDA attained 153% and 177% of its 28-day strength at 120 and 210 days respectively, and 15% OPC replacement with RHA-SDA attained 158% and 182% of its 28-day strength at 120 and 210 days respectively.
- v. The continued more rapid increase in strength of OPC-RHA-SDA composites compared to purely OPC composites (with 0% RHA-SDA) between 28 and 210 days suggests that some pozzolanic activity could still be going on at such later curing ages. Thus, OPC-RHA-SDA ternary blended cement structural members could be designed using some suitably higher strength values than the 28-day strength if they would not be fully loaded for some reasonable period after construction.

#### REFERENCES

- [1] B. H. A. Bakar, R. C. Putrajaya, and H. Abdulaziz, "Malaysian Saw dust ash – Improving the Durability and Corrosion Resistance of Concrete," *Pre-review. Concrete Research Letters*, vol. 1, no. 1, pp. 6-13, 2010.
- [2] V. N. Dwivedia, N. P. Singh, S. S. Das, and N. B. Singh, "A new pozzolanic material for cement industry: Bamboo leaf ash," *International Journal of Physical Sciences*, vol. 1, no. 3, pp. 106-111, 2006.
- [3] I. K. Cisse, and M. Laquerbe, "Mechanical characterization of sandcretes with rice husk ash additions: study applied to Senegal," *Cement and Concrete Research*, vol. 30, no. 1, pp.13– 18, 2000.
- [4] V. M. Malhotra, and P. K. Mehta, *Pozzolanic and Cementitious Materials*, London: Taylor & Francis, 2004.
- [5] K. Sakr, "Effects of Silica Fume and Rice Husk Ash on the Properties of Heavy Weight Concrete," *Journal of Materials in Civil Engineering*, vol. 18, no. 3, pp. 367-376, 2006.
- [6] I. O. Agbede, and S. O. Obam, "Compressive Strength of Rice Husk Ash-Cement Sandcrete Blocks," *Global Journal of Engineering Research*, vol. 7, no. 1, pp. 43-46, 2008.
- [7] S. Rukzon, and P. Chindaprasirt, "Strength of ternary blended cement mortar containing Portland cement, rice husk ash and fly ash," *J. Eng. Inst. Thailand*, vol. 17: pp. 547-551, 2006.
- [8] P. K. Mehta, and D. Pirtz, "Use of rice husk ash to reduce temperature in high strength mass concrete," *ACI Journal Proceedings*, vol. 75, pp. 60-63, 2000.
- [9] A. M. Fadzil, M. J. M. Azmi, A. B. B., Hisyam, and M. A. K. Azizi, "Engineering Properties of Ternary Blended Cement Containing Rice Husk Ash and Fly Ash as Partial Cement Replacement Materials," *ICCBT*, vol. A, no. 10, pp. 125 – 134, 2008.
- [10] G. C. Cordeiro, R. D. T. Filho, and E. D. R. Fairbairn, "Use of ultrafine rice husk ash with high-carbon content as pozzolan in high performance concrete," *Materials and Structures*, vol. 42, pp. 983-992, 2009.
- [11] A. U. Elinwa, S. P. Ejeh, and I. O. Akpabio, "Using metakaolin to



- improve sawdust-ash concrete," *Concrete International*, vol. 27, no. 11, 49 – 52, 2005.
- [12] A. U. Elinwa, S. P. Ejeh, and M. A. Mamuda, "Assessing of the fresh concrete properties of self-compacting concrete containing sawdust ash," *Construction and Building Materials Journal*, vol. 22, pp. 1178 – 1182, 2008.
- [13] A. U. Elinwa, and S. Abdulkadir, "Characterizing Sawdust-ash for Use as an Inhibitor for Reinforcement Corrosion," *New Clues in Sciences*, vol. 1, pp. 1-10, 2011.
- [14] L. O. Ettu, O. M. Ibearugbulem, U. C. Anya, C. T. G. Awodiji, and F. C. Njoku, "Strength of Binary Blended Cement Composites Containing Saw Dust Ash," *The International Journal of Engineering and Science (IJES)*, vol. 2, no. 4, pp. 51-56, 2013a.
- [15] L. O. Ettu, O. M. Ibearugbulem, K. O. Njoku, L. Anyaogu, and S. I. Agbo, "Strength of Ternary Blended Cement Sandcrete Containing Afikpo Rice Husk Ash and Saw Dust Ash," *American Journal of Engineering Research (AJER)*, vol. 2, no. 4, pp. 133-137, 2013b.
- [16] L. O. Ettu, O. M. Ibearugbulem, U. C. Anya, K. C. Nwachukwu, and C. T. G. Awodiji, "Strength of Blended Cement Soilcrete Containing Afikpo Rice Husk Ash and Saw Dust Ash," *International Journal of Engineering Research and Development (IJERD)*, vol. 7, no. 2, pp. 52-57, 2013c.
- [17] L. O. Ettu, J. C. Ezech, U. C. Anya, K. C. Nwachukwu, and K. O. Njoku, "Strength of Ternary Blended Cement Concrete Containing Afikpo Rice Husk Ash and Saw Dust Ash," *International Journal of Engineering Science Invention (IJESI)*, vol. 2, no. 4, pp. 38-42, 2013d.
- [18] P. K. Mehta, and P. J. M. Monteiro, *Concrete: Microstructure, Properties, and Materials*, 3<sup>rd</sup> ed. New York: McGraw-Hill Companies, 2006.
- [19] A. M. Neville, *Properties of Concrete*, 4th ed. London: Pearson Education Ltd, 2008.

IJSER